

ASTM E84-95

**SURFACE BURNING
CHARACTERISTICS**

Glasbord Kemply FRP Skin (.050")

Report No. 9013 - 100954

January 24, 1997

Prepared For:

Crane/Kemlite
23525 W. Eames Street
Channahon, IL 60410, U.S.A.



ABSTRACT

Test Material:	Glasbord Kemply FRP Skin (.050')		
Test Standard:	ASTM E84-95 Standard Test Method for SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS (ANSI 2.5, NFPA 255, UBC 8-1, UL 723)		
Test Date:	January 17, 1997		
Test Sponsor:	Crane/Kemlite		
Test Results:	FLAME SPREAD INDEX	=	100
	SMOKE DEVELOPED INDEX	=	115


The description of the test procedure and specimen evaluated, as well as the observations and results obtained, contained herein are true and accurate within the limits of sound engineering practice. These results are valid only for the specimen(s) tested and may not represent the performance of other specimens from the same or other production lots.

Omega Point Laboratories, Inc. authorizes the client named herein to reproduce this report only if reproduced in its entirety. The test specimen identification is as provided by the client and Omega Point Laboratories accepts no responsibility for any inaccuracies therein.



Javier Trevino
Manager, Standard Testing

Date: January 24, 1997



William E. Fitch, P.E. No. 55296
Executive Vice President

Date: January 24, 1997



I. INTRODUCTION

This report describes the results of the ASTM E84-95 Standard Test Method for SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS (1), a method for determining the comparative surface burning behavior of building materials. This test is applicable to exposed surfaces, such as ceilings or walls, provided that the material or assembly of materials, by its own structural quality or the manner in which it is tested and intended for use, is capable of supporting itself in position or being supported during the test period.

The purpose of the method is to determine the relative burning behavior of the material by observing the flame spread along the specimen. Flame spread and smoke density developed are reported, however, there is not necessarily a relationship between these two measurements.

“The use of supporting materials on the underside of the test specimen may lower the flame spread index from that which might be obtained if the specimen could be tested without such support... This method may not be appropriate for obtaining comparative surface burning behavior of some cellular plastic materials... Testing of materials that melt, drip, or delaminate to such a degree that the continuity of the flame front is destroyed, results in low flame spread indices that do not relate directly to indices obtained by testing materials that remain in place.”

This test method is also published under the following designations:

ANSI 2.5
NFPA 255
UBC 8-1 (42-1)
UL 723

This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use.

(1) American Society for Testing and Materials (ASTM), Committee E-5 on Fire Standards



II. PURPOSE

The ASTM E84-95 (25 foot tunnel) test method is intended to compare the surface flame spread and smoke developed measurements to those obtained from tests of mineral fiber cement board and select grade red oak flooring. The test specimen surface (18 inches wide and 24 feet long) is exposed to a flaming fire exposure during the 10 minute test duration, while flame spread over its surface and density of the resulting smoke are measured and recorded. Test results are presented as the computed comparisons to the standard calibration materials.

The furnace is considered under calibration when a 10 minute test of red oak decking will pass flame out the end of the tunnel in five minutes, 30 seconds, plus or minus 15 seconds. Mineral fiber cement board forms the zero point, while the red oak flooring flame spread and smoke developed ratings are set as 100.

III. DESCRIPTION OF TEST SPECIMENS

Specimen Identification: Glasbord Kemply FRP Skin (.050")

Date Received: 1/10/97

Date Prepared: January 10, 1997

Conditioning (73°F & 50% R.H.): 7 days

Specimen Width (in): 24

Specimen Length (ft): 24

Specimen Thickness: .05 in.

Material Weight: NA oz./sq. yd.

Total Specimen Weight: 17.43 lbs.

Adhesive or coating application rate: NA

Mounting Method:

The test specimen was self supporting.

Specimen Description:

The test specimen was described by the client as "Glasbord Kemply FRP skin (0.050 in.)". There were six sheets in the sample.



IV. TEST RESULTS

The test results, computed on the basis of observed flame front advance and electronic smoke density measurements are presented in the following table. In recognition of possible variations and limitations of the test method, the results are computed to the nearest number divisible by five, as outlined in the test method.

While no longer a part of this standard test method, the Fuel Contributed Value has been computed, and may be found on the computer printout sheet in the Appendix.

Test Specimen	Flame Spread Index	Smoke Developed
Mineral Fiber Cement Board	0	0
Red Oak Flooring	n/a	100
Glasbord Kemply FRP Skin (.050")	100	115

The data sheets are included in the Appendix. These sheets are actual print-outs of the computerized data system which monitors the ASTM E84 apparatus, and contain all calibration and specimen data needed to calculate the test results.

V. OBSERVATIONS

During the test, the specimen was observed to behave in the following manner:

The specimen had steady ignition at 0:32 (min:sec). The test continued for the 10:00 duration.

After the test, the specimen was observed to be damaged as follows:
The test specimen was completely consumed from 0 ft. - 22 ft.. There was dark discoloration from 22 ft. - 24 ft..



APPENDIX

DATA SHEETS



