

FRP Kemlite Fiberglass Cooling Tower Panels


Profile: **5.3 V-Beam Non-Fire-Rated**

Technical Data 6536

Weight: 8oz/ft², 12oz/ft², 16 oz/ft²

Color: 675 Light Gray

Product Code: 041CT



PROPERTIES	5.3 V-BEAM NON-FIRE-RATED	ASTM METHOD
Nominal Panel Weight	8oz/ft ²	—
Tensile Strength	11,000 psi	ASTM D638
Tensile Modulus	1,100,000 psi	ASTM D638
Flexural Strength	26,000 psi	ASTM D790
Flexural Modulus	600,000 psi	ASTM D790
Barcol Hardness	45	ASTM D2583
Light Transmission	< 5%	ASTM D1494
Flame Spread	N/A	ASTM E84
Burning Rate	3.5 in/min	ASTM D635
Burn Length	N/A	ASTM D635
U.B.C. Class	CC2	—

TOLERANCES (ALL PANELS)	
Panel Weight	±10%
Rib Height	±1/16
Length	±1/8
Width	±1/8

FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS
 The numerical flame spread and smoke development ratings are not intended to reflect hazards presented by Kemlite products or any other fire conditions. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test"). KEMLITE PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, frp may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated products and fire suppression system necessary for a specific installation.

CODES & APPROVALS

- ♦ASTM D-3841 - "Specification for Glass Fiber-Reinforced Polyester Plastic Panels".
- ♦CTI Code for Standard Specification, Bulletin STD-131- "Fiberglass Reinforced Plastic Panels for Application on Industrial Water Cooling Towers".

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.



www.kemlitect.com
 1-800-238-6874
 1-731-764-2153
 1-731-764-6397 fax

Kemlite Grand Junction Sales Office
 P.O. Box 569
 Grand Junction, TN 38039

CRANE Kemlite.
A Crane Co. Company
 Form 6536 (465)