

Industrial FRP Building Systems

ASSEMBLIES


PANELS

Form 6659
12/04

ISO-TUFF FIRE RATED LOAD SPAN TABLE

The information below is provided as preliminary data for designers. It should be checked and verified and its use determined by a duly licensed engineer or architect. NOTE: Spans will vary with resin formulation, glass content, and thickness. For data on other profiles, formulations, or conditions contact the technical department. Reference form #6473 for fastener requirements & locations


4.2" x 1-1/16"
GENERIC: 008IF



ROOFING: POSITIVE LOADS													LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF					
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN			
8 oz/sf	4' - 1"	5' - 5"	5' - 0"	3' - 7"	4' - 9"	4' - 5"	3' - 3"	4' - 3"	4' - 0"	3' - 0"	3' - 10"	3' - 8"	2' - 10"	3' - 6"	3' - 6"			
10 oz/sf	4' - 5"	5' - 10"	5' - 5"	3' - 10"	5' - 2"	4' - 9"	3' - 6"	4' - 8"	4' - 4"	3' - 3"	4' - 3"	4' - 0"	3' - 0"	3' - 10"	3' - 9"			
12 oz/sf	4' - 8"	6' - 3"	5' - 9"	4' - 1"	5' - 5"	5' - 0"	3' - 8"	4' - 11"	4' - 7"	3' - 5"	4' - 7"	4' - 3"	3' - 3"	4' - 3"	4' - 0"			
16 oz/sf	5' - 1"	6' - 10"	6' - 4"	4' - 6"	6' - 0"	5' - 6"	4' - 1"	5' - 5"	5' - 0"	3' - 9"	5' - 1"	4' - 8"	3' - 7"	4' - 9"	4' - 5"			

SIDING/ROOFING: WIND LOADS													LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Fasteners Required Every Other Corrugation					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF					
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN			
8 oz/sf	5' - 1"	6' - 4"	6' - 4"	4' - 6"	4' - 3"	4' - 10"	4' - 1"	3' - 2"	3' - 7"	3' - 9"	2' - 6"	2' - 11"	3' - 7"	2' - 1"	2' - 5"			
10 oz/sf	5' - 6"	7' - 5"	6' - 10"	4' - 10"	5' - 3"	5' - 11"	4' - 5"	4' - 0"	4' - 6"	4' - 1"	3' - 2"	3' - 7"	3' - 10"	2' - 8"	3' - 0"			
12 oz/sf	5' - 10"	7' - 10"	7' - 3"	5' - 1"	6' - 6"	6' - 4"	4' - 8"	4' - 10"	5' - 6"	4' - 4"	3' - 11"	4' - 5"	4' - 1"	3' - 3"	3' - 8"			
16 oz/sf	6' - 5"	8' - 8"	8' - 0"	5' - 8"	7' - 7"	7' - 0"	5' - 1"	6' - 10"	6' - 4"	4' - 9"	6' - 0"	5' - 11"	4' - 6"	5' - 0"	5' - 6"			


7.2" x 1-1/2"
GENERIC: 455IF



ROOFING: POSITIVE LOADS													LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF					
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN			
8 oz/sf	5' - 6"	7' - 5"	6' - 10"	4' - 10"	6' - 6"	6' - 0"	4' - 5"	5' - 9"	5' - 5"	4' - 1"	5' - 1"	5' - 0"	3' - 10"	4' - 8"	4' - 9"			
10 oz/sf	6' - 0"	8' - 0"	7' - 4"	5' - 3"	7' - 0"	6' - 5"	4' - 9"	6' - 4"	5' - 10"	4' - 5"	5' - 8"	5' - 5"	4' - 2"	5' - 2"	5' - 1"			
12 oz/sf	6' - 4"	8' - 6"	7' - 10"	5' - 6"	7' - 5"	6' - 10"	5' - 0"	6' - 9"	6' - 3"	4' - 8"	6' - 3"	5' - 9"	4' - 5"	5' - 8"	5' - 5"			
16 oz/sf	7' - 0"	9' - 4"	8' - 7"	6' - 1"	8' - 2"	7' - 6"	5' - 6"	7' - 5"	6' - 10"	5' - 2"	6' - 11"	6' - 4"	4' - 10"	6' - 6"	6' - 0"			

SIDING/ROOFING: WIND LOADS													LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Fasteners Required Every Corrugation					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF					
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN			
8 oz/sf	7' - 0"	7' - 5"	8' - 5"	6' - 1"	4' - 11"	5' - 7"	5' - 6"	3' - 8"	4' - 2"	5' - 2"	2' - 11"	3' - 4"	4' - 10"	2' - 6"	2' - 10"			
10 oz/sf	7' - 6"	9' - 3"	9' - 3"	6' - 7"	6' - 2"	7' - 0"	6' - 0"	4' - 7"	5' - 3"	5' - 6"	3' - 8"	4' - 2"	5' - 3"	3' - 1"	3' - 6"			
12 oz/sf	8' - 0"	10' - 8"	9' - 10"	7' - 0"	7' - 7"	8' - 7"	6' - 4"	5' - 8"	6' - 5"	5' - 11"	4' - 7"	5' - 2"	5' - 6"	3' - 9"	4' - 4"			
16 oz/sf	8' - 9"	11' - 9"	10' - 10"	7' - 8"	10' - 3"	9' - 6"	7' - 0"	8' - 9"	8' - 7"	6' - 6"	7' - 0"	8' - 0"	6' - 1"	5' - 10"	6' - 8"			


2.67" x 7/8"
GENERIC: 009IF



ROOFING: POSITIVE LOADS										LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	3' - 7"	4' - 9"	4' - 5"	3' - 1"	4' - 2"	3' - 10"	2' - 10"	3' - 9"	3' - 6"	2' - 7"	3' - 5"	3' - 3"	2' - 6"	3' - 2"	3' - 1"
10 oz/sf	3' - 10"	5' - 2"	4' - 9"	3' - 4"	4' - 6"	4' - 2"	3' - 1"	4' - 1"	3' - 9"	2' - 10"	3' - 9"	3' - 6"	2' - 8"	3' - 6"	3' - 3"
12 oz/sf	4' - 1"	5' - 6"	5' - 0"	3' - 7"	4' - 9"	4' - 5"	3' - 3"	4' - 4"	4' - 0"	3' - 0"	4' - 0"	3' - 8"	2' - 10"	3' - 9"	3' - 6"
16 oz/sf	4' - 6"	6' - 0"	5' - 6"	3' - 11"	5' - 3"	4' - 10"	3' - 7"	4' - 9"	4' - 5"	3' - 4"	4' - 5"	4' - 1"	3' - 1"	4' - 2"	3' - 10"

SIDING/ROOFING: WIND LOADS										LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Fasteners Required Every Third Corrugation					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	4' - 6"	6' - 0"	5' - 6"	3' - 11"	4' - 1"	4' - 8"	3' - 7"	3' - 1"	3' - 6"	3' - 4"	2' - 5"	2' - 9"	3' - 1"	2' - 0"	2' - 4"
10 oz/sf	4' - 10"	6' - 6"	6' - 0"	4' - 3"	5' - 1"	5' - 3"	3' - 10"	3' - 10"	4' - 4"	3' - 7"	3' - 1"	3' - 6"	3' - 4"	2' - 7"	2' - 11"
12 oz/sf	5' - 2"	6' - 11"	6' - 4"	4' - 6"	6' - 0"	5' - 6"	4' - 1"	3' - 8"	5' - 0"	3' - 9"	3' - 9"	4' - 3"	3' - 7"	3' - 2"	3' - 7"
16 oz/sf	5' - 8"	7' - 7"	7' - 0"	4' - 11"	6' - 7"	6' - 1"	4' - 6"	6' - 0"	5' - 6"	4' - 2"	5' - 5"	5' - 2"	3' - 11"	4' - 10"	4' - 10"


2.5" x 1/2"
GENERIC: 010IF



ROOFING: POSITIVE LOADS										LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	2' - 6"	3' - 4"	3' - 1"	2' - 2"	2' - 11"	2' - 8"	1' - 11"	2' - 7"	2' - 5"	1' - 10"	2' - 5"	2' - 3"	1' - 9"	2' - 4"	2' - 1"
10 oz/sf	2' - 8"	3' - 7"	3' - 3"	2' - 4"	3' - 1"	2' - 10"	2' - 1"	2' - 10"	2' - 7"	1' - 11"	2' - 7"	2' - 5"	1' - 10"	2' - 6"	2' - 3"
12 oz/sf	2' - 10"	3' - 9"	3' - 6"	2' - 6"	3' - 4"	3' - 1"	2' - 3"	3' - 0"	2' - 9"	2' - 1"	2' - 9"	2' - 7"	1' - 11"	2' - 7"	2' - 5"
16 oz/sf	3' - 1"	4' - 2"	3' - 10"	2' - 9"	3' - 8"	3' - 4"	2' - 6"	3' - 4"	3' - 1"	2' - 3"	3' - 1"	2' - 10"	2' - 2"	2' - 11"	2' - 8"

SIDING/ROOFING: WIND LOADS										LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Fasteners Required Every Third Corrugation					
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	3' - 1"	4' - 2"	3' - 10"	2' - 9"	3' - 8"	3' - 4"	2' - 6"	3' - 4"	3' - 1"	2' - 3"	3' - 10"	2' - 10"	2' - 2"	2' - 4"	2' - 8"
10 oz/sf	3' - 4"	4' - 6"	4' - 2"	2' - 11"	3' - 11"	3' - 7"	2' - 8"	3' - 7"	3' - 3"	2' - 6"	3' - 3"	3' - 1"	2' - 4"	2' - 11"	2' - 10"
12 oz/sf	3' - 7"	4' - 9"	4' - 5"	3' - 1"	4' - 2"	3' - 10"	2' - 10"	3' - 9"	3' - 6"	2' - 7"	3' - 6"	3' - 3"	2' - 6"	3' - 3"	3' - 1"
16 oz/sf	3' - 11"	5' - 3"	4' - 10"	3' - 5"	4' - 7"	4' - 3"	3' - 1"	4' - 2"	3' - 10"	2' - 11"	3' - 10"	3' - 7"	2' - 9"	3' - 8"	3' - 4"


7" x 1-1/2"
GENERIC: 2181F



ROOFING: POSITIVE LOADS							LIMITING CRITERIA:								
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	5' - 6"	7' - 5"	6' - 10"	4' - 10"	6' - 5"	5' - 11"	4' - 5"	5' - 8"	5' - 5"	4' - 1"	5' - 1"	5' - 0"	3' - 10"	4' - 8"	4' - 9"
10 oz/sf	5' - 11"	8' - 0"	7' - 4"	5' - 2"	6' - 11"	6' - 5"	4' - 9"	6' - 4"	5' - 10"	4' - 5"	5' - 8"	5' - 5"	4' - 1"	5' - 2"	5' - 1"
12 oz/sf	6' - 4"	8' - 6"	7' - 10"	5' - 6"	7' - 5"	6' - 10"	5' - 0"	6' - 9"	6' - 2"	4' - 8"	6' - 2"	5' - 9"	4' - 5"	5' - 8"	5' - 5"
16 oz/sf	6' - 11"	9' - 4"	8' - 7"	6' - 1"	8' - 2"	7' - 6"	5' - 6"	7' - 5"	6' - 10"	5' - 1"	6' - 10"	6' - 4"	4' - 10"	6' - 5"	5' - 11"

SIDING/ROOFING: WIND LOADS							LIMITING CRITERIA:								
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	6' - 11"	7' - 7"	8' - 7"	6' - 1"	5' - 0"	5' - 9"	5' - 6"	3' - 9"	4' - 4"	5' - 1"	3' - 0"	3' - 5"	4' - 10"	2' - 6"	2' - 10"
10 oz/sf	7' - 6"	9' - 5"	9' - 3"	6' - 6"	6' - 4"	7' - 2"	5' - 11"	4' - 9"	5' - 4"	5' - 6"	3' - 9"	4' - 4"	5' - 2"	3' - 2"	3' - 7"
12 oz/sf	7' - 11"	10' - 8"	9' - 10"	6' - 11"	7' - 9"	8' - 7"	6' - 4"	5' - 10"	6' - 7"	5' - 10"	4' - 8"	5' - 3"	5' - 6"	3' - 10"	4' - 5"
16 oz/sf	8' - 9"	11' - 9"	10' - 10"	7' - 8"	10' - 3"	9' - 5"	6' - 11"	9' - 0"	8' - 7"	6' - 5"	7' - 2"	8' - 0"	6' - 1"	6' - 0"	6' - 10"


5.33" x 1-3/4"
GENERIC: 0411F



ROOFING: POSITIVE LOADS							LIMITING CRITERIA:								
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	5' - 8"	7' - 7"	7' - 0"	4' - 11"	6' - 4"	6' - 1"	4' - 6"	5' - 6"	5' - 7"	4' - 2"	4' - 11"	5' - 2"	3' - 11"	4' - 6"	4' - 10"
10 oz/sf	6' - 1"	8' - 2"	7' - 7"	5' - 4"	7' - 1"	6' - 7"	4' - 10"	6' - 2"	6' - 0"	4' - 6"	5' - 6"	5' - 7"	4' - 3"	5' - 0"	5' - 3"
12 oz/sf	6' - 6"	8' - 8"	8' - 0"	5' - 8"	7' - 7"	7' - 0"	5' - 2"	6' - 9"	6' - 4"	4' - 9"	6' - 0"	5' - 11"	4' - 6"	5' - 6"	5' - 7"
16 oz/sf	7' - 2"	9' - 7"	8' - 10"	6' - 3"	8' - 4"	7' - 8"	5' - 8"	7' - 7"	7' - 0"	5' - 3"	6' - 11"	6' - 6"	4' - 11"	6' - 3"	6' - 1"

SIDING/ROOFING: WIND LOADS							LIMITING CRITERIA:								
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	7' - 2"	9' - 0"	8' - 10"	6' - 3"	6' - 1"	6' - 11"	5' - 8"	4' - 7"	5' - 2"	5' - 3"	3' - 8"	4' - 2"	4' - 11"	3' - 0"	3' - 5"
10 oz/sf	7' - 8"	10' - 0"	9' - 6"	6' - 9"	7' - 7"	8' - 4"	6' - 1"	5' - 8"	6' - 6"	5' - 8"	4' - 7"	5' - 2"	5' - 4"	3' - 9"	4' - 4"
12 oz/sf	8' - 2"	10' - 11"	10' - 1"	7' - 2"	8' - 11"	8' - 10"	6' - 6"	7' - 0"	7' - 11"	6' - 0"	5' - 7"	6' - 4"	5' - 8"	4' - 8"	5' - 4"
16 oz/sf	9' - 0"	12' - 1"	11' - 1"	7' - 10"	10' - 3"	9' - 9"	7' - 2"	8' - 11"	8' - 10"	6' - 8"	7' - 11"	8' - 2"	6' - 3"	7' - 2"	7' - 8"


4" x 1"
GENERIC: 1901F



ROOFING: POSITIVE LOADS								LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40							
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	4' - 3"	5' - 9"	5' - 4"	3' - 9"	5' - 0"	4' - 8"	3' - 5"	4' - 7"	4' - 2"	3' - 2"	4' - 2"	3' - 11"	3' - 0"	3' - 10"	3' - 8"
10 oz/sf	4' - 7"	6' - 2"	5' - 9"	4' - 0"	5' - 5"	5' - 0"	3' - 8"	4' - 11"	4' - 6"	3' - 5"	4' - 7"	4' - 2"	3' - 2"	4' - 3"	3' - 11"
12 oz/sf	4' - 11"	6' - 7"	6' - 1"	4' - 3"	5' - 9"	5' - 4"	3' - 11"	5' - 3"	4' - 10"	3' - 7"	4' - 10"	4' - 6"	3' - 5"	4' - 7"	4' - 2"
16 oz/sf	5' - 5"	7' - 3"	6' - 8"	4' - 9"	6' - 4"	5' - 10"	4' - 3"	5' - 9"	5' - 4"	4' - 0"	5' - 4"	4' - 11"	3' - 9"	5' - 0"	4' - 8"

SIDING/ROOFING: WIND LOADS								LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Fasteners Required Every Other Corrugation							
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	5' - 5"	6' - 1"	6' - 8"	4' - 9"	4' - 1"	4' - 7"	4' - 3"	3' - 1"	3' - 6"	4' - 0"	2' - 5"	2' - 9"	3' - 9"	2' - 0"	2' - 4"
10 oz/sf	5' - 10"	7' - 7"	7' - 2"	5' - 1"	5' - 1"	5' - 9"	4' - 7"	3' - 10"	4' - 4"	4' - 3"	3' - 1"	3' - 6"	4' - 0"	2' - 6"	2' - 11"
12 oz/sf	6' - 2"	8' - 4"	7' - 8"	5' - 5"	6' - 3"	6' - 8"	4' - 11"	4' - 8"	5' - 4"	4' - 7"	3' - 9"	4' - 3"	4' - 3"	3' - 2"	3' - 7"
16 oz/sf	6' - 10"	9' - 2"	8' - 5"	5' - 11"	8' - 0"	7' - 4"	5' - 5"	7' - 3"	6' - 8"	5' - 0"	5' - 9"	6' - 2"	4' - 9"	4' - 10"	5' - 6"

13.3" x 1-7/8"
GENERIC: 4611F



ROOFING: POSITIVE LOADS								LIMITING CRITERIA: Factor of Safety: 2.5 Deflection = L / 40							
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	5' - 10"	6' - 5"	7' - 2"	5' - 1"	5' - 3"	5' - 10"	4' - 6"	4' - 6"	5' - 1"	4' - 1"	4' - 1"	4' - 6"	3' - 8"	3' - 8"	4' - 2"
10 oz/sf	6' - 4"	7' - 2"	7' - 9"	5' - 6"	5' - 10"	6' - 6"	5' - 0"	5' - 1"	5' - 8"	4' - 6"	4' - 6"	5' - 1"	4' - 2"	4' - 2"	4' - 7"
12 oz/sf	6' - 8"	7' - 10"	8' - 3"	5' - 10"	6' - 5"	7' - 2"	5' - 4"	5' - 6"	6' - 2"	4' - 11"	4' - 11"	5' - 6"	4' - 6"	4' - 6"	5' - 1"
16 oz/sf	7' - 4"	9' - 0"	9' - 1"	6' - 5"	7' - 4"	7' - 11"	5' - 10"	6' - 4"	7' - 1"	5' - 5"	5' - 8"	6' - 4"	5' - 1"	5' - 2"	5' - 10"

SIDING/ROOFING: WIND LOADS								LIMITING CRITERIA: Factor of Safety: 1.88 Deflection = L / 20 Two Fasteners Required Every Corrugation							
	20 PSF			30 PSF			40 PSF			50 PSF			60 PSF		
	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN	1 SPAN	2 SPAN	3 SPAN
8 oz/sf	7' - 4"	7' - 5"	8' - 3"	6' - 1"	5' - 6"	6' - 3"	5' - 3"	4' - 2"	4' - 9"	4' - 8"	3' - 4"	3' - 9"	4' - 3"	2' - 9"	3' - 2"
10 oz/sf	7' - 11"	8' - 3"	9' - 3"	6' - 9"	6' - 9"	7' - 6"	5' - 10"	5' - 2"	5' - 11"	5' - 3"	4' - 2"	4' - 9"	4' - 9"	3' - 5"	3' - 11"
12 oz/sf	8' - 5"	9' - 0"	10' - 1"	7' - 4"	7' - 4"	8' - 3"	6' - 5"	6' - 5"	7' - 2"	5' - 9"	5' - 1"	5' - 10"	5' - 3"	4' - 3"	4' - 10"
16 oz/sf	9' - 3"	10' - 5"	11' - 6"	8' - 1"	8' - 6"	9' - 6"	7' - 4"	7' - 4"	8' - 2"	6' - 7"	6' - 7"	7' - 4"	6' - 0"	6' - 0"	6' - 8"

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.

Grand Junction Sales Office
 1-800-238-6874
 1-731-764-2153
 1-731-764-6316 fax
 E-Mail: industrialfrp@kemlite.com
 Website: www.industrialfrp.com

Kemlite is a registered trademark of Kemlite Company, Inc.

CRANE Kemlite.
A Crane Co. Company
 Form 6659 (1479)